

ESSENTIAL R4296

n-MP FREE WATERBORNE ALIPHATIC POLYURETHANE DISPERSION

Essential R4296 is an n-MP free, highly crystalline waterborne aliphatic polyurethane dispersion used for heat-activated adhesives. Essential R4296 can be used in a single-component, heat cured system or as a part of a 2-K curable system.

KEY BENEFITS

- Excellent adhesion to flexible PVC
- Block resistant
- Low temperature flexibility
- Toughness

DISCLAIMER: The information and recommendations contained herein are based on data believed to be correct. The information is offered solely for the customer's consideration, investigation and verification because of numerous factors beyond our control affecting the results of the use of products, Essential Industries, INC. makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for a particular purpose, other than that the product conforms to its applicable current standard specification. The manufacturer's only obligation shall be to replace such quantity of the product proven to be defective.

TYPICAL PROPERTIES*

Appearance	Translucent
pH.....	8.0
Solids, % by Weight	33.5
Solids, % by Volume	30.3
Viscosity, cP @ 25°C	50
Density Lbs./Gal.....	8.7
VOC Level (As Supplied)	
Lbs./Gal..	2.05
G/L.....	247
Partical Charge	Anionic
Partical Size.....	Colloidal
Acid Number	20
Freeze/Thaw Stable	Does Not Pass

*These values should not be interpreted as specifications.



**Essential[®]
Polymers**

The Spark of Innovation

Visit us on the web at
www.essentialpolymers.com

28391 Essential Road • P.O. Box 12
Merton, WI 53056-0012
(262) 538-0091 • FAX: (262) 538-1354