

ESSENTIAL R4300

N-MP-FREE URETHANE/ACRYLIC HYBRID

Essential R4300 is an aliphatic urethane/acrylic hybrid with incredible hardness. This solvent-free, low VOC polymer reaches a Konig Hardness of 180 secs within days of being applied. This polymer would be an excellent candidate to coatings that require high hardness, as well as, mar and scratch resistance properties.

KEY BENEFITS

- Very high hardness
- Mar and scratch resistance
- Low VOC

TYPICAL PROPERTIES*

Appearance	Opaque white
pH	8.0
Solids, % by Weight	35
Viscosity, cP @ 25°C -	
Brookfield, LV2, 60rpm	100
VOC Level (As Supplied)	
Lbs./Gal.	0.35
g/L	42
Particle Charge	Anionic
Konig Hardness (secs)	
1 Day	155
7 Day	180

**These values should not be interpreted as specifications.*

DISCLAIMER: The information and recommendations contained herein are based on data believed to be correct. The information is offered solely for the customer's consideration, investigation and verification because of numerous factors beyond our control affecting the results of the use of products. Essential Industries, INC. makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for a particular purpose, other than that the product conforms to its applicable current standard specification. The manufacturer's only obligation shall be to replace such quantity of the product proven to be defective.



Essential™
Polymers

The Spark of Innovation

Visit us on the web at
www.essentialpolymers.com

28391 Essential Road • P.O. Box 12
Merton, WI 53056-0012
(262) 538-0091 • FAX: (262) 538-1354